

Biotex Flax

Biotex Flax 100g/m² 2x2 Twill

Lightweight high performance fabric for sporting goods and decorative applications



Biotex Flax 100g/m² 2x2 Twill

Biotex Flax provides high levels of performance, coupled with the ease of processing normally associated with glass-reinforced materials. The materials use low-twist technology to provide a combination of sustainability, performance and processability. Compared to glass fibre composites, Biotex Flax offers reduced weight, improved environmental impact, vibration damping, similar specific stiffness and safer handling.

Biotex Flax is available in a range of yarn weights and fabric constructions. The materials can be processed using standard composites manufacturing techniques and are suitable for semi-structural and decorative applications in a range of sectors, including automotive, sports & leisure, consumer goods and construction.

Biotex Flax 100g/m² 2x2 Twill fabric is typically used for lightweight and decorative applications in sporting goods, consumer goods and automotive interiors.



Specifications

| | | |
|-----------------------|------------------------------------|-------------------|
| Weave Style | 2x2 Twill | |
| Fabric Weight | 100 g/m ² | |
| Width | 1500 mm | Others on request |
| Typical Ply Thickness | 0.15-0.25 mm, depending on process | |

Processing

Typical processes for Biotex Flax fabrics include vacuum infusion or resin transfer moulding using either standard resins or bio-based resins. The fabrics can also be pre-pregged, and processing is carried out in the same way as glass fibre.

Mechanical Properties

Typical mechanical properties of moulded laminates

| | | |
|-----------------------|------------------------|-----------|
| Fibre Volume Fraction | 24% | |
| Density | 1.27 g/cm ³ | |
| Tensile Modulus | 11 GPa | ISO 527-4 |
| Tensile Strength | 98 MPa | ISO 527-4 |
| Elongation | 1.3% | |
| Flexural Modulus | 8.7 GPa | ISO 14125 |
| Flexural Strength | 127 MPa | ISO 14125 |

Data from vacuum infused laminates using unsaturated polyester resin, tested at ambient temperature.

Safety

Biotex Flax reinforcements are based on renewable biomass and have fewer health and safety concerns than many conventional alternative materials. However, typical precautions should be taken when handling the material including using appropriate PPE and adequate ventilation.

Composites Evolution is a supplier of innovative, sustainable materials to the composites industry. Our products include fibres, resins and intermediates based on natural, bio-derived, recycled and recyclable materials, which enable customers to meet cost, weight and environmental targets.

- **Biotex Jute:** Low cost, lightweight alternative to glass fibre reinforcement
- **Biotex Flax:** High performance, lightweight alternative to glass and carbon fibres
- **Biotex Flax/PP:** Commingled reinforcement for rapid processing and reduced weight
- **Biotex Flax/PLA:** 100% bio-derived commingled reinforcement
- **Ecopreg PFA:** Fire-retardant prepreg with low environmental impact

Composites Evolution Ltd
4A Broom Business Park
Bridge Way, Chesterfield
S41 9QG, UK

T. +44 (0)1246 266248
F. +44 (0)1246 266249
info@compositesevolution.com

www.compositesevolution.com