

Biotex Flax

Biotex Flax 150g/m² Unidirectional Tape

High performance unidirectional tape for automotive, sporting goods and decorative applications



Biotex Flax 150g/m² Unidirectional Tape

Biotex Flax provides high levels of performance, coupled with the ease of processing normally associated with glass and carbon-reinforced materials. These highly aligned unidirectional tapes made direct from fibre offer a step change in performance for unit cost, especially when used as part of a multi-layer or hybrid layup, whilst providing the combination of sustainability, performance and processability associated with the Biotex range. Compared to glass fibre composites, Biotex Flax offers reduced weight, improved environmental impact, vibration damping, similar specific stiffness and safer handling.

Biotex Flax is also available in a range of yarn weights and fabric constructions. The materials can be processed using standard composites manufacturing techniques and are suitable for semi-structural and decorative applications in a range of sectors, including automotive, sports & leisure, consumer goods and construction.

Biotex Flax 150g/m² Unidirectional Tape is typically used for high-performance applications in sporting goods, automotive and general purpose components whilst offering an excellent cost to performance ratio.



Specifications

Format	Unidirectional tape	
Fabric Weight	150 g/m ²	
Width	180 mm	Others on request
Typical Ply Thickness	0.15-0.3 mm, depending on process	

Processing

Typical processes for Biotex Flax tapes include vacuum infusion or resin transfer moulding using either standard resins or bio-based resins. The tapes can also be pre-pregged, and processing is carried out in the same way as glass fibre.

Mechanical Properties

Typical mechanical properties of moulded laminates

	Vacuum infused unsaturated polyester	Press moulded epoxy prepreg	
Fibre Volume Fraction	28%	50%	
Density	1.25 g/cm ³	1.30 g/cm ³	
Tensile Modulus	20 GPa	30 GPa	ISO 527-4
Tensile Strength	198 MPa	222 MPa	ISO 527-4
Elongation	1.7%	1.5%	ISO 527-4
Flexural Modulus	20 GPa	23 GPa	ISO 14125
Flexural Strength	229 MPa	271 MPa	ISO 14125

Tested at ambient temperature.

Safety

Biotex Flax reinforcements are based on renewable biomass and have fewer health and safety concerns than many conventional alternative materials. However, typical precautions should be taken when handling the material including using appropriate PPE and adequate ventilation.

Composites Evolution is a supplier of innovative, sustainable materials to the composites industry. Our products include fibres, resins and intermediates based on natural, bio-derived, recycled and recyclable materials, which enable customers to meet cost, weight and environmental targets.

- **Biotex Jute:** Low cost, lightweight alternative to glass fibre reinforcement
- **Biotex Flax:** High performance, lightweight alternative to glass and carbon fibres
- **Biotex Flax/PP:** Commingled reinforcement for rapid processing and reduced weight
- **Biotex Flax/PLA:** 100% bio-derived commingled reinforcement
- **Ecopreg PFA:** Fire-retardant prepreg with low environmental impact

Composites Evolution Ltd
4A Broom Business Park
Bridge Way, Chesterfield
S41 9QG, UK

T. +44 (0)1246 266248
F. +44 (0)1246 266249
info@compositesevolution.com

www.compositesevolution.com